

Certificate of Analysis

Customer Name: CONTOUR HEATING PRODUCTS LIMITED
Certificate Number: BL002/2025

Date Received: 08.01.2025

Date Analysed: 14.01.2025

Date Reported: 20.01.2025

Tick box if customer has provided untreated control samples for inclusion in testing ☐

Test Method: Determination of Antibacterial Activity using Test Based on MOD ISO 22196: 2011

BioLabTests Sample Reference Number	Sample	Test Bacteria	Contact Time*		Reduction against Initial	
			0 Hrs	24 Hrs	Log ₁₀	%
250/027	BIOCOTE® PROTECTED PAINT	MRSA	9.13 x 10 ⁴	2.67 x 10 ²	2.53	99.71%
		<i>E. coli</i>	9.69 x 10 ⁴	≤100	≥2.99	≥99.90%

*Numbers represent Colony Forming Units at representative contact times.

Data show the changes in size of the initial MRSA (ATCC® 43300™) and *E. coli* (ATCC® 8739™) populations due to their contact with the treated surface of the samples. The samples detailed in this CoA were tested for 24 hours (±1) at 35°C (±2) under a relative humidity of >90% as specified in the ISO 22196 method. The results detailed in this CoA relate only to the items tested. This certificate shall not be reproduced except in full, without written approval of BioLabTests.

Please note; samples were received in a ready to test state from the customer apart from sterilisation which is noted below.
All testing is performed on site at the BioLabTests address above unless otherwise disclosed.



Noted during testing	
	Note
No. of samples supplied per test:	6 of 6 supplied
Sample size:	Average size: 50 x 50mm
Sample sterilisation method:	65°C DRY HEAT FOR ONE HOUR
Film size:	Average size: 40 x 40mm
Inoculation volume:	Volume: 0.1ml
Initial bacterial concentration:	MRSA: 9.13×10^5 CFU/ml <i>E. coli</i> : 9.69×10^5 CFU/ml

The material of the cover slips is polyethylene with a thickness of 0.045mm.

Please note – For all information regarding deviations from ISO 22196:2011, please request statement B-Lab-State-007



Richard Smith (BSc Hons)
Laboratory Manager,
BioLabTests Ltd

END OF REPORT

